

M.H

27.07.99

PCT/NL 99/00416

697220798




Europäisches  
Patentamt

European  
Patent Office

Office européen  
des brevets

16

NL 99/416



Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-  
gen stimmen mit der  
ursprünglich eingereichten  
Fassung der auf dem näch-  
sten Blatt bezeichneten  
europäischen Patentanmel-  
dung überein.

The attached documents  
are exact copies of the  
European patent application  
described on the following  
page, as originally filed.

Les documents fixés à  
cette attestation sont  
conformes à la version  
initialement déposée de  
la demande de brevet  
européen spécifiée à la  
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

98202232.9

## PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;  
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets  
p.o.

Arlotte Fiedler

A. Fiedler

DEN HAAG, DEN  
THE HAGUE,  
LA HAYE, LE

16/07/99

**THIS PAGE BLANK (USPTO)**



Europäisches  
Patentamt

European  
Patent Office

Office européen  
des brevets

**Blatt 2 der Bescheinigung**  
**Sheet 2 of the certificate**  
**Page 2 de l'attestation**

Anmeldung Nr.:  
Application no.:  
Demande n°: 98202232.9

Anmeldetag:  
Date of filing:  
Date de dépôt: 02/07/98

Anmelder:  
Applicant(s):  
Demandeur(s):  
Coöperatieve Verkoop- en Productievereniging van Aardappelmeel en Derivaten 'AVEBE' B.A.  
NL-9641 JA Veendam  
NETHERLANDS

Bezeichnung der Erfindung:  
Title of the invention:  
Titre de l'invention:  
Salt-stable modified starch

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat:  
State:  
Pays:

Tag:  
Date:  
Date:

Aktenzeichen:  
File no.  
Numéro de dépôt:

Internationale Patentklassifikation:  
International Patent classification:  
Classification internationale des brevets:

A23L1/0522, A23L1/187, A23L1/068, A23P1/16

Am Anmeldetag benannte Vertragsstaaten:  
Contracting states designated at date of filing: AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LI/LU/MC/NL/PT/SE  
Etats contractants désignés lors du dépôt:

Bemerkungen:  
Remarks:  
Remarques:

The original title of the application reads as follows:  
Salt-stable starch

**THIS PAGE BLANK (USPTO)**

02. 07. 1998

Eur4684

Title: Salt-stable starch

5

The invention relates to starch used in the food-industry.

Foodstuff is often thickened by the inclusion of a certain amount of starch as binder, filling or thickening agent, for example providing viscosity to a foodstuff during automated filling (canning).

For example, when industrially autoclaving or sterilising a food-stuff containing solid pieces, a certain filling viscosity is required while a container is being filled to prevent splashing of the liquid content over the rim of the container. Also, said viscosity provides an equal distribution of said solids during the filling phase. In canning, after filling, a decrease of viscosity is required, and any residual viscosity of the foodstuff after filling is considered unwanted for many applications. However, viscosity of starches in general is reduced during or after prolonged heat treatment, said reduction is in general aggravated by the presence of salts in the foodstuff.

Yet another reason to thicken a foodstuff is to provide said food with a better flavour, texture (mouthfeel) and appearance (looks).

Starch in itself has some flavour, that in general is appreciated by a customer, provided the foodstuff does not comprise too much starch which makes it taste starchy or cereal-like and provided a sensation of well-cooked starch is present, as opposed to an "undercooked" starch which gives a raw sensation. Most flavour in food, however, derives from (intricate combinations of) salts, proteins, short peptides, amino acids, fatty acids and

salts thereof, sugars, short and medium chain alcohols, and so on.

Texture of a starch comprising food is very much dependent on the degree of viscosity attained by adding  
5 varying degrees of starch. Aspects such as smoothness, firmness, cohesiveness, density, thickness, wateriness, cutability or spreadability, chewability and others can all depend on the viscosity and water retention properties provided by a starch. Too much cohesiveness is  
10 in general not appreciated, customers often prefer a more creamy, smooth texture. The choice of type of starch for use in foodstuff is greatly influenced by properties such as the stability during baking, deep-freezing, thawing and storage. It must furthermore be remembered that in  
15 general too much starch, although providing a desired viscosity, may change the flavour of the food negatively, in general there is a need to reduce starch dosage whenever this is made possible.

Appearance of a starch comprising foodstuff relates  
20 among others to the aspects mentioned with texture, however, starches often add opacity or cloudiness to food, making it look less palatable.

The above illustrates that, within the food industry, use of starch, for each and every different  
25 application, often comprises finding the right balance between too little and too much, in trying to find a product with attractive palatability.


A distinct problem herein is the fact that starches in themselves have reduced stability to the effects of  
30 certain salts, ions or electrolytes present in food. For example, a starch may initially provide a desired texture (such as smoothness, firmness, cohesiveness, density, thickness, wateriness, cutability or spreadability, chewability) to a foodstuff, which then, however, loses  
35 said texture, cohesiveness or smoothness in time because the salt-stability of the starch used is too low or

inappropriate. The product becomes watery, falls apart and separates into wet and less wet fractions, leaks flavours, in general loses its appearance and texture, and loses its attraction to a customer. Said loss of texture or appearance is in general caused by a too low stability to salts, electrolytes, cations or anions, or other constituents of food, and necessitates increasing the starch dosage, often with detrimental effects on taste.

The effects of salts on starch have been investigated for more than a century (see for examples: Starch: Chemistry and Technology. Eds. Whistler and Paschall, Academic Press, New York and London).

The gelatinization of starch and starch derivatives in the presence of medium to high concentrations of electrolytes has been studied extensively (B.J. Oosten, Die Staerke 31, 228-230 (1979); B.J. Oosten, Die Staerke 32, 272-275 (1980); B.J. Oosten, Die Staerke 34, 233-239 (1982); B.J. Oosten, Die Staerke 35, 160-169 (1983); B.J. Oosten, Die Staerke 42, 327-330 (1990)). In low concentration systems the properties of solutions of polymers in the presence of electrolytes can be adequately accounted for by electrostatics, taking into account only the magnitude of the ionic charge, the concentration and the solvent. Biological systems are usually more concentrated and specific ion-solvent effects will dominate the solution properties.

Some electrolytes promote gelatinization and some electrolytes inhibit the process. Promotion or inhibition mainly follow the well known Hofmeister or lyotropic series (F. Franks in "Water", Royal Society of Chemistry Paperbacks London 1983). This series are a listing of the order in which they affect polymer (and therefor starch) solubility. An example of such a series is:



Electrolytes on the left ( $\text{CNS}^-$ ,  $\text{ClO}_4^-$ ,  $\text{I}^-$ ,  $\text{NO}_2^-$ ) promote and on the right ( $\text{Cl}^-$ ,  $\text{F}^-$ ,  $\text{HPO}_3^{2-}$ ,  $\text{SO}_4^{2-}$ ) inhibit gelatinisation.

5        This series can of course be extended with other anions and similar series can be listed for cations, although in general the effects observed for cations are smaller than for anions. A completely satisfying explanation for the observed phenomena for this series  
10 has not been reported so far, but the general believe is that electrolytes on the right side enhance water structure thus favouring solvent-solvent interactions over starch-solvent interactions (Franks 1983). This induces a hampered gelatinisation and lack of stability  
15 of starches in water.

Neutral components, such as hydrocolloids, ureum, sorbitol, caseine, and sugars such as sucrose, fructose, galactose, and others have similar effects on the stability of starch as salts. It has for example been  
20 found that neutral components like saccharides (sugars) effect the viscosity of strach and derivatives (I.D. Evans, D.R. Haisman, Die Staerke 34, 224-231 (1982)). The effects have been contributed to the same phenomena as seen with salts, notably the effects reported on water  
25 structure are similar.

The application of starch derivatives in food systems is usually accompanied by the addition of electrolytes, mainly chlorides and phosphates. Especially  
~~chlorides and phosphates inhibit the development or~~  
30 stability of viscosity of starch and starch derivatives.

A special case is the addition of calcium ions to potato starch and potato starch derivatives. Potato starch contains bound monophosphate ester groups. In water these phosphate groups give the starch backbone  
35 negative charge resulting in a high viscosity as compared to other starches. When calcium ions are added they form



a relatively insoluble complex with the phosphate groups resulting in a sharp decrease in viscosity.

Thus, although salt-instability of starch is relatively well understood, the problem remains, starches  
5 currently used in the food-industry generally have low-stability to salts compromising at least the palatability, texture, appearance and other related aspects of foodstuffs.

10 The invention provides modified starch, and derivatives derived thereof, having improved salt-stability (salt-stable starch), use of such modified starch or derivatives derived from said starch in foodstuff, a method for providing salt-stability to  
15 foodstuff comprising use of such modified starch or derivatives derived from said starch and foodstuff comprising said modified starch or derivatives derived from said starch.

The invention provides a method for improving a  
20 foodstuff comprising adding to said foodstuff a salt-stable starch. Such a starch has improved stability to salts and other components that are detrimental to the stability of a common starch. The invention for example provides a method for improving the texture of a  
25 foodstuff, e.g. the cohesiveness of relatively solid foods such as meats or meat products or puddings or the smoothness of relatively liquid products such as soups, sauces, creams or fillings. The invention provides a method wherein said salt-stable starch is a non-cereal  
30 starch, for example derived from tubers or roots, containing essentially only amylopectin molecules.

The invention provides a method for providing a foodstuff with a desired texture comprising adding to said foodstuff a modified starch obtained from for  
35 example tubers or roots, said starch containing essentially only amylopectin molecules. A modified starch

is a native starch treated in such a way as to modify one or more of its physical or chemical properties. Modified starches have remained their starch character. The native or raw starches are modified to produce starch products with desirable properties. Starches, both of the common variety containing both amylose and amylopectin, obtained from both cereals and tubers or roots and of the waxy variety, containing essentially only amylopectin molecules (e.g. 0-5% amylose), obtained from cereals, are widely used in foodstuff.

Common starch consists of two major components, an, in essence, linear  $\alpha(1-4)$ D-glucan polymer (branching is found at a low level) and an elaborately branched  $\alpha(1-4$  and  $1-6)$ D-glucan polymer, called amylose and amylopectin, respectively. Amylose has, in solution, a helical conformation with a molecular weight of  $10^4 - 10^5$ . Amylopectin consists of short chains of  $\alpha$ -D-glucopyranose units primarily linked by (1-4) bonds with (1-6) branches and with a molecular weight of up to  $10^7$ .

Amylose/amylopectin ratios in native starches in plants are generally anywhere at 10-40 amylose/90-60% amylopectin, also depending on the variety of plant studied. In a number of plant species mutants are known which deviate significantly from the above mentioned percentages. These mutants have long been known in maize (corn) and some other cereals. Waxy corn or waxy maize has been studied since the beginning of this century. Therefore, the term waxy starch has often been equated with amylose free starch, despite the fact that such starch was in general not known from other starch sources such as potato but mainly derived from corn. Furthermore, industrial use of an amylose free potato starch has never occurred on a large scale and with such a wide range of applications as waxy starch. The invention provides a method according to the invention wherein said starch has superior salt-stability over a common starch. For

example, the invention provides a modified cross-linked starch having superior stability over a common starch when tested in a sodium chloride solution, or when tested in a solution containing calcium ions, which seriously  
5 effect the viscosity of a common potato starch. Another example of the invention is a modified starch according to the invention which provides a meat brine, a foodstuff used in preparing meat products, with increased and more stable water binding properties than a common starch  
10 would do. Also, the addition of a milk protein, such as caseine which has viscosity inhibiting properties, or derivative thereof to a foodstuff no longer compromises the texture of said foodstuff when a modified starch according to the invention is added to said foodstuff.

15 The invention provides a method wherein said modified starch containing essentially only amylopectine molecules has been derived from a genetically modified plant. Amylose production in a plant is among others regulated by the enzyme granule-bound starch synthase  
20 (GBSS), which is involved in generating the amylose content of starch, and it has been found that many of the waxy cereal mutants described above lack this enzyme or its activity, thereby causing the exclusive amylopectin character of these mutants.

25 An example of a salt-stable starch provided by the invention is a starch obtained from an amylose-free potato plant which is for example lacking GBSS activity or GBSS protein altogether, thereby lacking amylose and having essentially only amylopectin molecules.

30 In a preferred embodiment of the invention, a method is provided wherein the starch is derived from a genetically modified plant such as a potato, yam, manihot or cassave. Genetic modification of such tuber or root plants is a skill available to the artisan, and for  
35 example involves modification, deletion of or insertion in or (antisense) reversion of (parts of) a gene, such as

a gene encoding granule-bound starch synthase (GBSS), which is involved in determining the amylose content of starch. In order to manipulate such crop plants, efficient transformation systems and isolated genes are available, especially of potato, and others are found by analogy. Traits, such as absence of amylose, that are introduced in one variety of a crop plant can easily be introduced into another variety by cross-breeding.

In the experimental part of this description, a method is provided wherein said modified starch is obtained from a genetically modified potato.

In a preferred embodiment, a method and a modified starch are provided wherein said starch is a crosslinked starch. Crosslinking starch is in itself a method available to the artisan, various cross-linking agents are known, examples are epichlorohydrin, sodium trimetaphosphate, phosphorous oxychloride, chloroacetic acid, acrolein, dichloro acetic acid, adipic anhydride or other reagents with two or more anhydride, halogen, halohydrin, epoxide or glycidyl groups or combinations thereof which all can be used as crosslinking agents. A typical example of such a cross-linked starch is starch mono-phosphate.

Furthermore, the invention provides a starch which is stabilised. Stabilisation by hydroxyalkylation or carboxymethylation of starch is for example obtained with reagents containing a halogen, halohydrin, epoxide or glycidyl group as reactive site. Chloro acetic acid (or its salt) is used as carboxymethylation reagent. In one embodiment of the invention said starch is stabilised by hydroxypropylation, hydroxybutylation, hydroxyethylation and/or carboxymethylation.

In yet another embodiment of the invention, said starch is a stabilized starch in which some or all of the available hydroxyl groups of the amylopectin molecules have been esterified by acetyl groups. The addition of

acetyl groups is generally done in aqueous suspensions of starch using acetic anhydride or vinyl acetate as reactants under alkaline conditions.

5 A modified starch as provided by the invention is preferably derived from root or tuber-derived amylose-free or amylopectin native starches such as obtainable from potato starch, tapioca, sweetroot starch, yam starch, canna starch or manihot starch. In a preferred embodiment of the invention such a root or tuber starch  
10 is derived from a genetically modified plant, for example from a genetically modified potato plant variety. Examples of such a potato plant variety are the variety Apriori or Apropect, or varieties derived thereof.

In a much preferred embodiment, the invention  
15 provides modified starch comprising a starch obtained from tubers or roots, said starch containing essentially only amylopectin molecules, and derivatives derived thereof, having improved salt-stability (salt-stable starch), use of such modified starch or derivatives  
20 derived from said starch in foodstuff, a method for providing salt-stability to foodstuff comprising use of such modified starch or derivatives derived from said starch and foodstuff comprising said modified starch or derivatives derived from said starch.

25 Use of starch from genetically engineered crops has in general been suggested from the time on it was possible to genetically modify such crops (see i.e. Bruinenberg et al., Chemistry and Industry, 6 November 1995, page 881-884; de-Vries, Foodmarketing and  
30 Technology, April 1997, page 12-13)). Specific use of amylopectin-type potato starch as filling or viscosity agent in canning has been suggested in WO/97/03573 to prevent undesired residual viscosity seen with commonly used starch. Furthermore, EP 0 796 868 suggests use of  
35 hydroxypropylated and highly cross-linked waxy potato starch to increase the viscosity of a food product.

However, none of these provide indications on how to avoid using starches in the food-industry which generally have low-stability to salts and compromise at least the palatibility, texture, appearance and other related aspects of foodstuffs. To the contrary, for example WO/97/03573 suggests an amylopectin-type potato starch which maintains its viscosity only for a certain period, after which no residual viscosity is left, suggesting that these types of products are less stable instead, and EP 0 796 868 suggests using said hydroxypropylated and highly cross-linked waxy potato starch under conditions of high temperature, low temperature and high shear, again conditions, such as aseptic filling, retorting or freezing, where fill viscosity may be needed and salt stability is no issue.

In a preferred embodiment, the invention provides a method according to the invention wherein said modified starch is an instant starch. In general starch and starch derivatives for the food industry are insoluble in cold water. Viscosity and water binding is achieved by heating or cooking. These starches are referred to as cook-up starches. For convenience starches are sometimes pregelatinised i.e. precooked and dried. These starches are referred to as instant starches and perform without heating or cooking in the food stuff. Pre-gelatinisation can be achieved by spray cooking, spray drying, roll drying, drum drying, extrusion, heating in aqueous water miscible organic solvents or under high pressure or with other methods known in the art.

Furthermore, the invention provides a method wherein said foodstuff comprises at least 0.1(w/w)%, preferably at least 0.5 or 1(w/w)% or even at least 2-10(w/w)% of a sodium salt or combinations of sodium salts, for example wherein said salt comprises sodium chloride or for example wherein said salt comprises sodium-mono-glutamate (vetsin).

Also, the invention provides a method wherein said foodstuff comprises at least 0.5(w/w)%, preferably at least 1 or 2(w/w)% or even at least 10-20(w/w)% of a milk protein or derivative thereof for example wherein said  
5 protein is caseine.

Furthermore, the invention provides a method wherein said foodstuff comprises at least 0.5(w/w)%, preferably at least 1(w/w)% or even at least 3-5(w/w)% of a calcium salt, for example wherein said salt is calcium chloride.

10 Furthermore, the invention provides a method wherein said foodstuff comprises at least 5(w/w)%, preferably at least 10(w/w)%, more preferably at least 20(w/w)% or even at least 30-70(w/w)% of a sugar, for example wherein said sugar is sucrose.

15 In the experimental part of this description examples are given of improved foodstuffs according to the invention, wherein various salts, and other components, such as milk protein or sugars, or combinations thereof, are used at various concentrations  
20 in combination with a starch according to the invention which provides the desired texture to said foodstuff.

Yet another embodiment of the invention is a method wherein said foodstuff is a meat brine, which is a foodstuff in itself (however in general not intended for  
25 primary consumption) and used for example for preparing a meat product. Such a meat brine is in general used to improve the texture of a meat product.

The invention further provides a modified starch for use in a method according to the invention. Examples of  
30 such a modified starch are described herein above and in the experimental part of the invention.

Furthermore, the invention provides foodstuff obtainable by a method according to the invention. For example, the invention provides a meat brine comprising a  
35 modified starch as provided by the invention.

The invention is further described in the experimental part of the description without limiting the invention thereto.

## 5 Experimental part

### Example 1

Stability of cross-bonded or cross-linked, acetylated  
10 regular potato starch (PS), is influenced negatively when applied in salt containing formulations foodstuffs, however, the invention provides products based on amylopectin potato starch (APS) which are more viscosity or water retention stable than regular potato starch  
15 derivatives. Especially products that have been developed for meat or meat product applications, such as meat injection brine, used for example for preparing or injecting meats such as ham or poultry products, such as "thanksgiving" turkey. Possible products are regular  
20 potato starch derivatives for example crosslinked with sodiumtrimetaphosphate and acetylated with acetic anhydride and are herein compared with amylopectin potato starch (APS) derivatives. APS was crossbonded with the same amount of NaTMP as PS and stabilized with acetic  
25 anhydride. The products were characterised on Brabender gelatinisation in demineralised water (as is) and in 1% NaCl solution.

### Materials

30

- A - Regular potato starch derivative
- B - Amylopectin potato starch derivative
- C - Regular potato starch derivative
- D - Amylopectin potato starch derivative

35

The crosslinking of A, B, C and D with NaTMP and esterification with acetic anhydride were done according to routine procedures.



- E - Regular potato starch derivative  
F - Amylopectin potato starch derivative

- 5 The crosslinking of E and F with POCl<sub>3</sub>, was done according to routine procedures.

- 10 The products were characterised by Brabender gelatinization. Gelatinisation was measured of a 3% (dry matter) suspension with a Brabender viscograph, type E at 250 cmg in demineralized water. Gelatinisation behaviour was also measured in a 1% NaCl solution.

- 15 Table 1 : Brabender gelatinisation, as is and in 1% NaCl solution, Brabender type E, 250 cmg, 75 rpm, 3% (dry matter).

Product	Starch	Brabender suspension	Tg °C	Tpeak °C	BUpeak	Brabender BU at °C			
						75°	00'90°	10'90°	20'90°
A	PS	as is	59,5	--	--	795	1405	1825	1915
B	APS	as is	60,5	73,0	3110	2800	2730	2520	2410
A	PS	1% NaCl	61,5	--	--	35	110	155	175
B	APS	1% NaCl	62,0	--	--	940	1010	1080	1095
C	PS	as is	59,5	--	--	805	1335	1710	1800
D	APS	as is	64,5	--	--	1515	1735	1805	1820
C	PS	1% NaCl	61,0	--	--	65	145	200	220
D	APS	1% NaCl	66,0	--	--	125	365	1065	1290

PS = Potato starch, APS = Amylopectin potato starch

- 20 Viscosity levels in demineralised water of the regular potato starch based products do not differ much. Also it becomes clear that Product D based on APS has the same end viscosity as its potato starch counterpart, but the temperature of gelatinisation is much higher. The product  
25 B based on APS has still a peak viscosity. From the table it can be noticed that the APS based products are more

salt stable than the regular PS based products. The end viscosity levels of the samples prepared with potato starch and the APS counterparts do not differ upon gelatinisation in demineralised water. Product B and D.

5 based on amylopectin potato starch provide better stability in the salt solution than the samples prepared with regular potato starch and can therefor be used at lower concentrations.

10 In table 2, similar effects of  $\text{POCl}_3$  cross-linked starch ethers are shown.

Table 2. Brookfield viscosity of the products E and F as is and in 1% NaCl solution Brookfield : RVDV II+ #5, 50 rpm

Product	Starch	Crossl.	Amount per kg	Subst.	DS	Solution	Viscosity mPas
E	PS	$\text{POCl}_3$	19.5 $\mu\text{L}$	HP	0.15	as is	6150
F	APS	$\text{POCl}_3$	19.5 $\mu\text{L}$	HP	0.15	as is	4400
E	PS	$\text{POCl}_3$	19.5 $\mu\text{L}$	HP	0.15	1% NaCl	1960
F	APS	$\text{POCl}_3$	19.5 $\mu\text{L}$	HP	0.15	1% NaCl	2450

15 Reduction in viscosity of regular potato starch derivative: 70%

Reduction in viscosity of Amylopectin potato starch: 40%

20 Viscosity of regular starch derivative in water (as is) is higher than APS derivative. In salt solution the reverse is observed.

#### Example 2

25 Viscosity measurement of cross-linked instant starch derivatives in deionized water, 5%(w/w) sodium casein solution and 1%(w/w)  $\text{CaCl}_2$  solution

30 Weight 10 gram of the product. Add 212 ml of the desired solution while the mixture is stirred by hand. Then the mixture is stirred for 1 minute using a Ultra-Turrax at a

speed of 4000 rpm. After 29 minutes the dispersion is again stirred by hand for  $\frac{1}{4}$  minute and then the viscosity is measured using a Brookfield LVF at 6 rpm with spindle no. 4. Viscosity is determined for increasing degree of cross-linking. For results compare, figures 1, 3, 4.

### Example 3

Viscosity measurement of instant starch derivatives in the presence of milk powder.

Weigh 10 gram product and 28 gram milk powder. Add 212 ml de-ionised water while the mixture is stirred by hand. Then the mixture is stirred for 1 minute using a Ultra-Turrax at a speed of 4000 rpm. After 29 minutes the dispersion is again stirred by hand for  $\frac{1}{4}$  minute and then the viscosity is measured using a Brookfield LVF at 6 rpm with spindle no. 4. Viscosity is determined for increasing degree of cross-linking. For results compare, figures 1, 2.

### Example 4

#### Water binding

25

Meat injection brines are injected into whole muscle meats. They provide a desired texture to the meat by dissolving meat proteins that coagulate upon heating. Starch is used to bind water in order to increase the 'pump level' (the amount of water incorporated in the meat product) and texture of the product. They also play a preserving role because of the salt content of the brine. In these experiments water is used to replace meat, in order to get a realistic approximation of the content of the different ingredients. The ingredients of the meat injection brine are as follows:

	demineralised water	480 g
	salt	8 g
	starch	5.5 g
	dextrose	4 g
5	sodium phosphate	2.5 g

The water binding capacity of the brine is measured as follows. The ingredients are mixed and put in a Brabender  
10 viskograph. The initial temperature of the Brabender is set on 30°C, the mixture is heated till 75°C with a slope of 1.5°C/min. After staying 5 min at 75°C, the temperature decreases till 25° with a slope of 3°C/min. The mixture is removed from the Brabender and 400 ml is transferred into  
15 2 transparent centrifuge tubes and centrifuged for 15 min at 894 g and 25°C. The separation line between the pellet and the sediment and the supernatant is marked and hereafter the tubes are emptied and dried. Then the tubes are filled with water till the mark; the weight of the  
20 water is the sediment volume. The water binding capacity can be expressed in ml sediment per g starch. At least two repeats of each starch sample are done. The standard deviation is 5 ml sediment/500 ml on average, which is reasonable compared to a mean of 78 ml  
25 sediment/500 ml.

In Figure 5 the water binding of three cross-bonded hydroxypropylated derivatives is shown. The water binding is expressed in ml per g of starch. Farinex VA 15 is a  
30 product based on regular potato starch, HW 3294 is a product based amylopectin potato starch and B-990 is a product based on maize starch. The grey bars on the left are the water binding capacities in demineralised water, the black bars on the right are the capacities in brine.  
35 As can be seen from the figure, in demineralised water the binding capacity of the products based on potato starch and amylopectin potato starch are about the same. The water binding capacity of the product based on maize starch is much lower.

In brine the binding capacity of the amylopectin based derivative is essentially the same as in water. Only a drop of less than 9 % in the binding capacity is observed. The potato based (30 %) and the corn based products (23 %) show a much larger drop in water binding capacity.

#### Example 6

Viscosity measurements of starch derivatives in the presence of sugar.

It has been found that neutral components like saccharides (sugars) affect the viscosity of starch and derivatives (I,D. Evans, D.R. Haisman, Die staerke 34, 224-231 (1982)). The effects have been contributed to the same phenomena as with salts (water structure).

Example 6 provides the effects on viscosity of using APS derived starch in sugar solutions.

Addition of relatively large amounts of sucrose to common starch causes a decrease in viscosity. Quite surprisingly, amylopectin potato starch derivatives show the opposite effect, as is demonstrated in table 3.

Table 3.

Product	Starch	Brab. susp.	TG	Tpeak	Bupeak	Brabender BU at °C		
						75°	00'90°	20'90°
A	PS	as is	59.5	--	--	795	1405	1915
B	APS	as is	0.5	73.0	3110	2800	2730	2410
A	PS	30% suc.	61.5	--		360	920	1320
B	APS	30% suc.	63.0	73	4960	4800	3920	3520

Examples of improved foodstuff according to the invention.

### Instant fruit filling

5

Ingredients:	%	g
Instant modified starch	33.3	15.0
Powdered sugar	66.7	30.0

10

Preparation procedure:  
 - the dry ingredients are blended  
 - the powdered mix (45 g) is added to 200 ml fruit juice and stirred (low speed) for 1 minute.

15

### Instant lemon whipped dessert

Ingredients:	%
Powdered sugar	32.0
Instant skimmed milk powder	22.2
Whippable Fat Powder	22.0
Starch derivative	22.0
Lemon Flavour	1.0
Citric acid	0.5
25 Colour	0.3

Use 50 g dry mix to 150 mL of cold water

### 30 Fat-free bologna

Recipe for fat-free bologna

Ingredients:	%
35 Lean port (1.2% - 1.5% fat)	28.55
Lean turkey (0.7% fat)	24.37
Water	27.30
Modified starch	7.62
Dextrose	3.13
40 Salt	2.12
Milk protein hydrolysate	2.06
Bologna flavouring/seasoning	1.79
Sodium lactate	1.25
Turkey stock (dry)	0.38
45 Sodium tripolyphosphate	0.25
Cure-all (6.25% of NaNO <sub>2</sub> )	0.12

Low-fat hot dogs

Ingredients:		%
	B90 Lean Beef	39.17
5	B65 Fat Beef	9.36
	Water	1.27
	Salt	2.05
	Sodium Tripolyphosphate (TSP)	0.243
	Sucrose	1.69
10	Beef Frankfurter Seasoning	2.20
	Cure salt (contains 6.25% sodium nitrite)	0.121
	Sodium Erythorbate	0.022
	Ground Mustard	0.58
	Modified starch	3.38
15	Total raw meat mix:	100.0

Vending soup

Ingredients:		%	g
20	Instant modified starch	2.6	5.5
	Bouillon powder	1.9	4.0
	Water	95.5	200.0

## Preparation procedure:

- weigh the dry components in a 250 ml beaker
- add hot water and stir

Instant pudding

Ingredients:		%	g
	Instant modified starch	24.2	20.0
35	Powdered sugar	48.5	40.0
	Dextrose monohydrate	24.2	20.0
	Tetrasodium pyrophosphate	2.0	1.8
	Calcium acetate	1.0	0.8
	Colour/vanilla flavour	0.1	0.4

## Preparation procedure:

- the dry ingredients are blended
- the powdered mix (80 g) is added to 500 ml cold milk and stirred for 1 minute using an electric hand-mixer (high speed)
- pour the pudding into dessert-trays and place them into the refrigerator for 30 minutes

Bilberry pie filling

## Ingredients:

		%	g
	A		
	sugar	19.0	47.5
5	modified starch	5.4	13.5
	salt	0.2	0.5
	B		
	bilberry juice	30.0	75.0
	water	45.4	113.5
10	Total:	100.0	250.0

## Preparation procedure:

- mix the dry components (mix A)
- 15 - mix bilberry juice and water in a pan (mix B)
- add mix A to mix B and suspend with a whisk
- heat until boiling whilst stirring with a whisk
- keep boiling for 1 minute

20

UHT lobster soup

## Ingredients:

		%
	Milk	12.1
25	Cream	6.0
	Lobstermix**	5.1
	Lecimulthin 100*	0.02
	Instant modified starch	4.3
	Water	72.48

30

- \* Supplier Lucas Meyer
- \*\* Supplier Rieber & Son

## Processing steps for lobster soup:

- 35 - Preheating to 70°C in a PHE
- Homogenisation at 50 bar
- Sterilisation at 135°C
- Holding for 28 seconds
- Cooling to 20°C in tubes (20 QC heb ik veranderd in °C)
- 40 - Filling temperature 20°C



Recipe UHT spicy soup

	Ingredients:	%
	Salt (NaCl)	0.8
5	Butter	0.6
	Tomato paste	12.5
	Instant modified starch	2.0
	Spice mix	0.8
	Chicken bouillon	0.2
10	Lecimulthin 100*	0.03
	Water	83.07

\* Supplier Lucas Meyer

- 15 Processing steps for tomato soup:
- Preheating to 70°C in a PHE
  - Homogenisation at 50 bar
  - Sterilisation at 135°C
  - Holding for 28 seconds
  - 20 - Cooling to 20°C in tubes
  - Filling temperature 20°C

Instant bakery cream

	Ingredients:	%	g
25	Instant modified starch	20.0	80.0
	Whole milk powder	30.0	120.0
	Powdered sugar	47.5	130.0
30	Alginate blend	2.25	20.0
	Colour/vanilla flavour	0.25	1.0

Preparation procedure:

- the dry ingredients are blended
- 35 - the powdered mix (400 g) is added to 1000 ml tap water and stirred for 3 minutes using an Hobart mixer (high speed)

## Figures

Figure 1. Viscosity measurement of cross-linked instant starch derivatives in deionized water.

5

Figure 2. Viscosity measurement of cross-linked instant starch derivatives in a milky solution, here prepared by adding milk powder.

10 Figure 3. Viscosity measurement of cross-linked instant starch derivatives in 1% (w/w)  $\text{CaCl}_2$  solution.

Figure 4. Viscosity measurement of cross-linked instant starch derivatives in 5% (w/w) sodium casein solution.

15

Figure 5. Water binding properties of cross-linked hydroxylpropylated starch derivatives in water and in brine.

02. 07. 1998

## Claims

1. A method for improving a foodstuff comprising adding to said foodstuff a salt-stable starch.
- 5 2. A method according to claim 1 wherein the texture of said foodstuff is improved.
3. A method according to claim 1 or 2 wherein said starch is a non-cereal starch containing essentially only amylopectin molecules.
- 10 4. A method according to any one of claims 1 to 3 wherein said starch is derived from a genetically modified plant.
5. A method according to claim 4 wherein said plant is a potato.
- 15 6. A method according to any one of claims 1 to 5 wherein said starch is a cross-linked starch, such as a phosphorus oxytrichloride or sodium trimataphoshate cross-linked starch.
7. A method according to any one of claims 1 to 6 wherein  
20 said starch is a stabilised starch, such as a hydroxyalkylated or acetylated starch.
8. A method according to any one of claims 1 to 7 wherein said starch is an instant starch.
9. A method according to any one of claims 1 to 8 wherein  
25 said foodstuff comprises at least 0.1(w/w)%, preferably at least 0.5 (w/w)%, more preferably at least 1 (w/w)% of a sodium salt.
10. A method according to claim 9 wherein said salt is sodium-chloride.
- 30 11. A method according to claim 9 wherein said salt is sodium monoglutamate.
12. A method according to any one of claims 1 to 8 wherein said foodstuff comprises at least 0.5(w/w)%, preferably at least 1(w/w)% of a milk protein or  
35 derivative thereof.

13. A method according to claim 12 wherein said protein is caseine.

14. A method according to any one of claims 1 to 8 wherein said foodstuff comprises at least 0.5(w/w)%, preferably at least 1(w/w)% of a calcium salt.

15. A method according to claim 14 wherein said salt is calcium chloride.

16. A method according to any one of claims 1 to 8 wherein said foodstuff comprises at least 5(w/w)%, preferably at least 10(w/w)%, more preferably at least 20(w/w)% of a sugar.

17. A method according to claim 16 wherein said sugar is sucrose.

18. A method according to any one of claims 1 to 17 wherein said foodstuff is a meat brine.

19. A modified starch for use in a method according to any one of claims 1 to 18.

20. A foodstuff obtainable by a method according to any one of claims 1 to 18.

02. 07. 1998

## Abstract

The invention relates to starch used in the food-  
industry. The invention provides modified starch, and  
5 derivatives derived thereof, having improved salt-  
stability (salt-stable starch), use of such modified  
starch or derivatives derived from said starch in  
foodstuff, a method for providing salt-stability to  
foodstuff comprising use of such modified starch or  
10 derivatives derived from said starch and foodstuff  
comprising said modified starch or derivatives derived  
from said starch.

**THIS PAGE BLANK (USPTO)**



Figure 1 : Brookfield viscosity in deionized water  
Brookfield LVF, 6 rpm, spindle 4

EPO-DG 1

02. 07. 1998




Figure 2 : Brookfield viscosity in milk  
Brookfield LVF, 6 rpm, spindle 4




Figure 3 : Brookfield viscosity in 1%  $\text{CaCl}_2$   
Brookfield LVF, 6 rpm, spindle 4






Figure 4 : Brookfield viscosity in 5 % Caseine (Sodium salt)  
Brookfield LVF, 6 rpm, spindle 4





Left, water; right, brine



Figur 5

**THIS PAGE BLANK (USPTO)**